

HIGH GLOSS FLOOR FINISH

RENO2819-MS
(107455)
RENO2820-MS
(107456)
RENO2930-MS

Features:

- Excellent Gloss
- Can be spray buffed or burnished
- Resists scuffs, abrasions, and black heel marks

Description:

This combination sealer/polish delivers excellent gloss and outstanding durability. The latest floor care polymer technology provides ease of use and even application of finish onto most floor surfaces. Can be spray buffed or burnished; easy to remove with conventional stripper solutions. Resists scuffs, abrasions, black heel marks and offers outstanding chemical resistance.

Directions:

PREPARATION: If stripping is necessary, use a high quality product and follow directions accordingly. If floor is in good condition and stripping is not necessary, sweep up excess dirt and dust and then clean with a good quality cleaner to remove dirt and oils. Follow with a thorough rinsing and allow to dry completely.

FINISHING: If floor was stripped, use a good acrylic sealer to further prepare the floor for finishing. Spread a liberal coat of finish evenly across the floor with a clean mop or applicator. Allow each coat to dry at least 30 minutes before applying the next coat. Two or three coats are desired initially, depending on the condition of the floor and gloss desired.

MAINTENANCE: The floor may be maintained using a quality floor cleaner and damp mopping regularly. Spray buffing or mop-on restoring may also be done after sweeping up loose dirt and dust. Follow directions for each product accordingly.

This product meets the maximum content requirements for Volatile Organic Compounds (VOCs) as established by State and Federal regulations.

TECHNICAL INFORMATION:	
Type:	Modified acrylic
Non-volatile Solids:	18.0±0.5%
Color:	Milky white
Odor:	Mild
pH:	8.5 - 9.0
Dry/Recoat Time:	30 minutes min.
Slip Resistance:	0.5 min. by ASTM D2047
Gloss:	90+ specular
Leveling:	Excellent
Buffability:	Spray buff or restorer
Removability:	With conventional strippers
Detergent Resistance:	Excellent
Waterspot Resistance:	Excellent
Heel Mark Resistance:	Excellent
VOC Content:	0.31 lbs./gal.
Storage/Stability:	2 years
Freeze/Thaw Stability:	Keep from freezing
Weight per Gallon:	8.56 lbs./gal.
Coverage:	2000-2500 ft ² per gal.

